



# CHLOROMARK

## CHLORINATED RUBBER ROAD MARKING PAINT

A high quality, alkyd modified chlorinated rubber paint that is specially designed for road marking. As a road marking paint to draw parking bay lines, arrows, numbers, lines etc. Suitable for use on bituminous and concrete surfaces.

Technical Data	
Finish	Matt
Volume solids	approx. 35 %
Dry film thickness (DFT)	75 micron per coat
Wet film thickness (WFT)	100 micron per coat
Number of coat	1-2
Theoretical Coverage	8.0 sq. mt/ltr per cot @ 75 micron DFT
Drying time	Surface Dry : 30 min

### Advantages

- Very tough and abrasion resistant.
- Excellent weather durability.
- Resistant to petrol, diesel, engine oil, water etc.
- Fast drying.

### Method of Use:

- Clean the Kerb surface thoroughly removing all dust, oil grease and paint.
- Ensure the Kerb surface is completely dry and free from moisture.
- Cold and humid conditions require a longer drying time. Such conditions should be avoided.
- Temperature at the time of application should not be above 60°C and below 10°C.
- Humidity should not be above 85%.

### Method of Application:

- Brush or roller these are the recommended method of application.
- Stir contents of the can thoroughly before use. Thinning is usually required. However, if thinning is desired, do not exceed the recommended thinning ratio.
- Clean all equipment immediately after use with Solvent. Dried paint on equipment could be removed by ketonic solvents.

### Drying Time :

Substrate Temperature	Touch Dry	Hard dry	Over coating Interval	
			Minimum	Maximum
15	45 minutes	2 hrs	8 hrs	Indefinite
25	30 minutes	1 hrs	4 hrs	Indefinite
35	15 minutes	30 min	1 hrs	Indefinite

## AUTOMARK INDUSTRIES (INDIA) PVT. LTD.



Corporate Office :-  
2nd & 3rd Floor, 2, Lotus Plaza, Opposite VCA Stadium,  
Gate No. 2, Civil Lines, Nagpur - 440001.(M.S)  
India.  
PH# +91 0712 6603687/680/6615768 email :- [info@automark-india.com](mailto:info@automark-india.com)  
Fax3 +91 0712 6603679 Site : [www.automark-india.com](http://www.automark-india.com)  
Plant : At post Bothali village, Behind Islamic Madarasa, Wardha Road, Nagpur - 441108  
CIN - U24290MH2002PTC135673

**Additional Information**

Thinner-27

Thinning ratio 15% maximum

Cleaning solvent Thinner-27

Flash point > 10<sup>o</sup> C

Storage requirement store in cool, dry area away from direct sunlight.

**Mixing:**

- Thorough mixing should be done before application.

**Colours:** White and Golden yellow

**Packing:** 20 Ltr.

**AUTOMARK INDUSTRIES (INDIA) PVT. LTD.**

Corporate Office :-

2<sup>nd</sup> & 3<sup>rd</sup> Floor, 2, Lotus Plaza, Opposite VCA Stadium,

Gate No. 2, Civil Lines, Nagpur – 440001.(M.S)

India.

PH# +91 0712 6603687/680/6615768 email :- [info@automark-india.com](mailto:info@automark-india.com)

Fax3 +91 0712 6603679

Site : [www.automar-india.com](http://www.automar-india.com)

Plant : At post Bothali village,Behind Islamic Madarasa.Wardha Road,Nagpur – 441108

CIN – U24290MH2002PTC135673